

# ANALYSIS REPORT

Sample Submitted : PET COKE .

<b>SPECIFICATION (ESPECIFICACIONES)</b>	<b>UOM (UNID)</b>	<b>TETS METHOD (METODO DE ENSAYO)</b>	<b>TYPICAL (TIPICO)</b>	<b>MIN</b>	<b>MAX</b>	<b>TYPE (TIPO)</b>
GROSS CALORIFIC VALUE HARDGROVE GRINDABILITY INDEX	BTU/LB	D2015 D409		14000 50	14.500 80	
<b>MOISTURE</b>	<b>WTPCT</b>	<b>D3173D3302</b>		6	12	
<b>SIZE LESS THAN 2CM</b>	<b>PCT</b>	<b>D293</b>			65	
<b>SIZE LESS THAN 5CM</b>	<b>PCT</b>	<b>D293</b>			100	
<b>SULPHUR (DRY BASIS)</b>	<b>WT PCT</b>	<b>D4249D4239</b>		4	5.5	
<b>VANADIUM &amp; METALS CONTENT IN COK</b>	<b>PPM</b>	<b>D3683</b>		1000	3000	
<b>VOLATILE MATTER (DRY BASIS)</b>	<b>PCT</b>	<b>D4421</b>		9	14	
<b>ASHES (DRY BASIS) SIZE (COKER RUN, GRINDED TO)</b>	<b>PCT</b>			0.5 2	1 4	